MAGIC TOUCH® FILM



ULTRA SATIN

PHYSICAL PROPERTIES

Top Coating **Polyoptico™**	Elongation (ASTMD-882) **450%**	Chemical Resistance (Acid Test) **Pass**	Impact Test (SEA J400) **Pass**
Film Thickness **190 µm**	Aging Resistance (UV Test6000H) **Pass**	60° Surface Gloss **21**	Hydrophobic Angle) **107°**
Warranty **10 Years**	Tensile Stength (ASTMD-882) **30Mpa**	Tear Stength (ASTMD-882) **80 N/cm**	Initial Peel Adhesion (ASTMD-882) **20 N/in**